

---

**APPROVED SOURCES  
CONCRETE SEALERS FOR SPECIFIED BRIDGE DECK AREAS**

\*All surfaces to be sealed must be sound, clean and DRY.

<b><u>MANUFACTURER</u></b>	<b><u>BRAND NAMES</u></b>	<b><u>COVERAGE RATE</u></b>	<b><u>MIN. SURFACE TEMP. °C (°F)</u></b>
Conspec	Spec Seal	1 or 2 coats 2.5 m <sup>2</sup> /L (100 ft. <sup>2</sup> /gal.)	10 (50)
Euclid Chemical Company	Dural 335	2.45 m <sup>2</sup> /L (100 ft. <sup>2</sup> /gal.)	4 (40)
L & M Construction	Pentox 50	2 coats 1st coat 4.91 m <sup>2</sup> /L (200 ft. <sup>2</sup> /gal.) 2nd coat 7.36 m <sup>2</sup> /L (300 ft. <sup>2</sup> /gal.)	10 (50)
Poly-Carb, Inc.	Mark-87	2 coats 1st coat Mark-87 2.95 m <sup>2</sup> /L (120 ft. <sup>2</sup> /gal.) 2nd coat Mark-87 2.45 m <sup>2</sup> /L (100 ft. <sup>2</sup> /gal.)	10 (50)
Star, Inc. (McConnell & Assoc.)	Star Macro-Deck	7.36 m <sup>2</sup> /L/ (300 ft. <sup>2</sup> /gal.)	4 (40)
Steelcote Mfg. Company	PE-50 Penetrating Sealer	1.96 m <sup>2</sup> /L (80 ft. <sup>2</sup> /gal.)	4 (40)
Symons Corporation	R-130 Penetrant Sealer	2 coats 7.36 m <sup>2</sup> L (300 ft. <sup>2</sup> /gal.) each coat	0 (32)

---

<b><u>MANUFACTURER</u></b>	<b><u>BRAND NAMES</u></b>	<b><u>COVERAGE RATE</u></b>	<b><u>MIN. SURFACE TEMP. °C (°F)</u></b>
TK Products	TK-2671 Penetrating Sealer	2 coats 9.82 m <sup>2</sup> /L (400 ft <sup>2</sup> /gal) each coat	4 (40)
Unitex	Bridge Seal	1 coat 2.5 m <sup>2</sup> /L (100 ft. <sup>2</sup> /gal.)	4 (40)
Viking Paints, Inc.	TE-3008-1	2 coats 9.82 m <sup>2</sup> /L (400 ft. <sup>2</sup> /gal.) each coat	4 (40)