

**APPROVED SOURCES
 NON-CHLORIDE ACCELERATING ADMIXTURES**

<u>BRAND NAME</u>	<u>PRODUCER/DISTRIBUTOR</u>	<u>RECOMMENDED MINIMUM DOSAGE</u>	
		<u>mL/kg cementitious materials</u>	<u>fl. oz./100 lb. cementitious materials</u>
Accelguard NCA	Euclid Chemical Company	7.8	12.0
CATEXOL 2000 RHE	Axim	6.5	10.0
Daraset 400	W.R. Grace & Company	6.5	10.0
DCI	W.R. Grace & Company	See Manufacturer's Recommendation	
Lubricon NCA (Also acts as a water reducer)	W.R. Grace & Company	6.5	10.0
NCA	Friz-Pak Corporation	1% by weight of cement*	
Plastocrete 161FL	Sika Corporation	3.9	6.0
Polarset	W.R. Grace & Company	5.2	8.0
Polychem Super See	General Resource Technology	5.2	8.0
Polychem Super See III	General Resource Technology	5.2	8.0
Plychem Super Set	General Resource Technology	5.2	8.0
Pozzolith NC 534	BASF Admixtures, Inc.	10.4	16.0
Pozzutec 20	BASF Admixtures, Inc.	3.3	5.0
Pozzutec 20+	BASF Admixtures, Inc.	3.3	5.0
Rheocrete CNI	BASF Admixtures, Inc.	See Manufacturer's Recommendation	
Sika Rapid-1	Sika Corporation	5.2	8.0
SikeSet NC	Sika Corporation	6.5	10.0

*Dry-powdered admixture pre-packed in water-soluble bag