



**DEVELOPMENTAL SPECIFICATIONS
FOR
ALTERNATE ACCEPTANCE OF HMA FOR LOCAL SYSTEMS PROJECTS**

**Effective Date
October 16, 2012**

THE STANDARD SPECIFICATIONS, SERIES 2012, ARE AMENDED BY THE FOLLOWING MODIFICATIONS AND ADDITIONS. THESE ARE DEVELOPMENTAL SPECIFICATIONS AND THEY SHALL PREVAIL OVER THOSE PUBLISHED IN THE STANDARD SPECIFICATIONS.

This Specification becomes void on federal aid contracts. Apply requirements of Article 2303 of the Standard Specifications unless otherwise stated.

For mixture bid items not defined as small quantities in Article 2303.03, D, of the Standard Specifications, acceptance for laboratory voids will be based on a moving absolute average deviation (AAD) from target as defined in Materials I.M. 501. Use the production tolerance in Table 2303.03-5.

2303.03, D, 4, a 6, b.

Replace the Article:

For all other areas of Class I compaction, determine PWL, as defined in Materials I.M. 501, for each lot using a lower specification limit (LSL) of 3.5% voids (96.5% of G_{mm}) and an upper specification limit (USL) of 8.5% voids (91.5% G_{mm}).

2303.05, A, 3, b, 1.

Replace the Article:

Payment when PWL is used for acceptance:

PWL	Pay Factor
95.1 – 100.0	$PF = 0.008000 * PWL + 0.240$
80.0 – 95.0	1.000
50.0 – 79.9	$PF = 0.008333 * PWL + 0.3333$
Less than 50.0	0.750

When PWL is less than 50.0, the Engineer may declare the lot or parts of the lot deficient or unacceptable.