



**DEVELOPMENTAL SPECIFICATIONS
FOR
HOT MIX ASPHALT THIN LIFT OVERLAY**

**Effective Date
June 17, 2014**

THE STANDARD SPECIFICATIONS, SERIES 2012, ARE AMENDED BY THE FOLLOWING MODIFICATIONS AND ADDITIONS. THESE ARE DEVELOPMENTAL SPECIFICATIONS AND THEY PREVAIL OVER THOSE PUBLISHED IN THE STANDARD SPECIFICATIONS.

12055.01 DESCRIPTION.

These specifications describe the requirements for a highly polymer modified asphalt thin lift surface course. Apply Section 2303 of the Standard Specifications unless otherwise directed in these specifications. Not for use on interstate roadways.

12055.02 MATERIALS.

A. Asphalt Binder.

Use a PG+ 76-34 with a minimum 90% elastic recovery when RTFO-aged per AASHTO T 240 and tested per AASHTO T 301 at 77°F (25°C).

B. Mix Design.

1. See Materials I.M. 510 Appendix A.
2. 50% of the total aggregate shall be Friction Type 4.
3. Mix approval is based on Performance Testing Requirements per Table 5 in Materials I.M. 510 Appendix A.

12055.03 CONSTRUCTION.

- A.** Apply a tack coat prior to placement of the thin lift overlay.
- B.** Compact with steel wheeled roller.
- C.** Do not open to traffic until the entire mat has cooled below 150°F (65°C).
- D. Quality Assurance/Quality Control.**

1. Field Voids Acceptance.

Acceptance for field voids shall be Class II compaction defined in Section 2303 of the Standard Specifications.

2. Lab Voids Acceptance.

Sample and test one hot box per day of production unless otherwise approved by the Engineer. Apply Article 2303.05, A, 3, a, 2, of the Standard Specifications for AAD acceptance. Air void target is based on approved JMF.

3. Take at least one cold feed for gradation control.

12055.04 METHOD OF MEASUREMENT.

Hot Mix Asphalt Thin Lift Overlay, of the size specified, will be measured according to Article 2303.04 of the Standard Specifications.

12055.05 BASIS OF PAYMENT.

Hot Mix Asphalt Thin Lift Overlay, of the size specified, will be paid for according to Article 2303.05 of the Standard Specifications.