



**SPECIAL PROVISIONS  
FOR  
GRANULAR SUBBASE**

**Franklin County  
IMX-035-6(140)172--02-35**

**Effective Date  
February 18, 2025**

**THE STANDARD SPECIFICATIONS, SERIES 2023, ARE AMENDED BY THE FOLLOWING MODIFICATIONS AND ADDITIONS. THESE ARE SPECIAL PROVISIONS AND THEY SHALL PREVAIL OVER THOSE PUBLISHED IN THE STANDARD SPECIFICATIONS.**

The requirements for granular subbase from Section 2111 of the Standard Specifications are modified as follows:

1. Use material meeting the following revised gradation:

<b>Standard Sieve Size</b>										
<b>1 1/2"</b>	<b>1.00"</b>	<b>3/4"</b>	<b>1/2"</b>	<b>3/8"</b>	<b>4</b>	<b>8</b>	<b>30</b>	<b>50</b>	<b>100</b>	<b>200</b>
<b>Percent Passing</b>										
100			40-80			10-35				2-8

2. Compact granular subbase with six passes of a self-propelled, vibratory steel roller per Article 2001.05, F of the Standard Specifications. The Engineer may direct fewer passes based on their assessment and/or testing of material degradation, consolidation, and permeability.